

Specialty Films Selection Guide

		Specialty Films		
Properties ¹		9960	9962	9967
1. Sterilization ²	(G=Gamma; E=Ethylene Oxide)	G	G	G, E
2. Hypoallergenic				Yes
3. Printable Backing		Yes	Yes	Yes
4. Fluid Resistance		Yes	Yes	Yes
5. Heat Sealable		No	No	Yes
6. Light Transmission	percentage	90	92	N/A
7. Haze Level, maximum	percentage	2.5	1.5	N/A
8. Color		Clear	Clear	Transparent
9. Typical Tensile, MD	lbs/inch	166	85 Minimum	15
	Newtons/25mm	738	378	66.7
10. Elongation, minimum	percentage	70	90	100
11. Film/Liner Caliper	mil	6.8	3.9	2.0
	millimeters	0.17	0.10	0.05
12. Maximum Width	inches	49	49	52
	centimeters	124.5	124.5	132
13. Maximum Length	yards	1600	2600	1500
	meters	1463	2377	1372
14. Approx. Roll Diameter	inches	22	21	12.5
	centimeters	56	53	32
15. Shelf Life	months	14	14	24

¹ Properties listed are based on limited testing and for comparative purposes only. It is the customer's responsibility to determine the final suitability of our products for use in their application.

² Recommended suitability is based on the processability of product through typical sterilization conditions. It is the customer's responsibility to determine the final suitability of our products for use in their application.

Table Revised August 2013